



Trademark
SOUNDPROOFING

GUILFORD OF MAINE - QUADRILLE

PRODUCT SPECS

Specifications

Contents

47% pre-consumer recycled polyester
53% polyester

Weight

12.11 ± 1.0 oz./lin. yd.

Width

54" useable

Repeat

none

Treatment

none

Backing

none

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Performance



Breaking Strength (ASTM D5034)

271.5 lbf min. warp and 249.5 lbf min fill

Tear (ASTM D2261)

28.2 lbf min. warp and 27 lbf min fill

Seam Slippage (ASTM D4034)

73 lbf warp and 91.3 lbf fill

Pilling resistance (ASTM D3511)

Class 4

Colorfastness to light (AATCC 16 Option 3)

Grade 4 at 40 hours

Colorfastness to crocking (AATCC 8)

Grade 4 dry & Grade 4 wet

Wyzenbeek Abrasion resistance (ASTM D4157)

100,000 double rubs cotton duck

Flammability

CA Technical Bulletin 117-2013 Section 1

NFPA 260/UFAC Fabric Classification - Class I

ASTM E84 Class I or A



Miscellaneous

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Proudly woven in North America supporting our local communities.

Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

www.tmsoundproofing.com

Phone: 845-388-1200 Fax: 845-388-1388